

Amendments

Please enter the following amendments:

In the Claims

Sub D1
1. (Amended) A method of encapsulation of at least one islet cell, comprising the steps of:

- a) creating a mix of the at least one islet cell, which is first encapsulated in a microcapsule, in an aqueous macromer solution comprising macromer and photoinitiator;
- b) forming small globular geometric shapes of the mix; and
- c) polymerizing the macromer by exposing the geometric shapes to light radiation.

Full
1:126
Sub D2
2. (New) The method of claim 1, wherein the macromer is a water soluble, ethylenically unsaturated, polymer susceptible to polymerization into a water insoluble polymer through interaction of at least two carbon-carbon double bonds.

3. (New) The method of claim 2, wherein the macromer is selected from the group consisting of ethylenically unsaturated derivatives of poly(ethylene oxide) (PEO), poly(ethylene glycol) (PEG), poly(vinyl alcohol) (PVA), poly(vinylpyrrolidone) (PVP), poly(ethyloxazoline) (PEOX), poly(amino acids), polysaccharides, and proteins.

4. (New) The method of claim 3, wherein the PEG is PEG tetraacrylate.

5. (New) The method of claim 3, wherein the polysaccharides are selected from the group consisting of alginate, hyaluronic acid, chondroitin sulfate, dextran, dextran sulfate, heparin, heparin

Sub 132
133
sulfate, heparan sulfate, chitosan, gellan gum, xanthan gum, guar gum, water soluble cellulose derivatives and carrageenan.

6. (New) The method of claim 3, wherein the proteins are selected from the group consisting of gelatin, collagen, and albumin.

134
7. (New) The method of claim 1, wherein the photoinitiator is any dye that absorbs light having a frequency between 320 nm and 900 nm, can form free radicals, is at least partially water soluble, and is non-toxic to the at least one islet cell at the concentration used for polymerization.

135
8. (New) The method of claim 1, wherein the macromer solution further comprises a primary, secondary, tertiary, or quaternary amine cocatalyst and the photoinitiator is selected from the group of ethyl eosin, eosin Y, fluorescein, 2, 2-dimethoxy, 2-phenylacetophenone, 2-methyl, 2-phenylacetophenone, camphorquinone, rose bengal, methylene blue, erythrosin, phloxime, thionine, riboflavin, and methyl green.

136
9. (New) The method of claim 1, wherein the geometric shapes are formed by coextrusion of the aqueous macromer solution mixed with the biological material with a non-toxic, non-immunogenic, non-miscible substance capable of maintaining droplet formation.

137
10. (New) The method of claim 1, wherein the microcapsule is comprised of material selected from the group of alginate, chitosan, agarose, and gelatin.

Sub 138
11. (New) The method of claim 1, wherein the macromer solution further comprises an accelerator to increase the rate of polymerization.

139
12. (New) A method for encapsulation of at least one islet cell, which is first encapsulated in a microcapsule, comprising the steps of:

- CS
Rule 1126.
- (a) coating at least one islet cell with photoinitiator;
 - (b) suspending the at least one coated islet cell in a macromer solution comprised of macromer; and
 - (c) irradiating the suspension with light.

140
13. (New) The method of claim 12, wherein the macromer is a water soluble, ethylenically unsaturated, polymer susceptible to polymerization into a water insoluble polymer through interaction of at least two carbon-carbon double bonds.

141
14. (New) The method of claim 13, wherein the macromer is selected from the group consisting of ethylenically unsaturated derivatives of poly(ethylene oxide) (PEO), poly(ethylene glycol) (PEG), poly(vinyl alcohol) (PVA), poly(vinylpyrrolidone) (PVP), poly(ethyloxazoline) (PEOX), poly(amino acids), polysaccharides, and proteins.

142
15. (New) The method of claim 14, wherein the polysaccharides are selected from the group consisting of alginate, hyaluronic acid, chondroitin sulfate, dextran, dextran sulfate, heparin, heparin sulfate, heparan sulfate, chitosan, gellan gum, xanthan gum, guar gum, water soluble cellulose derivatives and carrageenan.

Sub 143
cont.
143
16. (New) The method of claim 14, wherein the proteins are selected from the group consisting of gelatin, collagen, and albumin.

C2
144
17. (New) The method of claim 12, wherein the photoinitiator is any dye that absorbs light having a frequency between 320 nm and 900 nm, can form free radicals, is at least partially water soluble, and is non-toxic to the at least one islet cell at the concentration used for polymerization.

Rule 1.12d
145
18. (New) The method of claim 12, wherein the macromer solution further comprises a primary, secondary, tertiary, or quaternary amine cocatalyst and the photoinitiator is selected from the group of ethyl eosin, eosin Y, flurorescein, 2, 2-dimethoxy, 2-phenylacetophenone, 2-methyl, 2-phenylacetophenone, camphorquinone, rose bengal, methylene blue, erythosin, phloxime, thionine, riboflavin, and methyl green.

144
19. (New) The method of claim 12, wherein the microcapsule is comprised of material selected from the group of alginate, chitosan, agarose, and gelatin.

147
20. (New) The method of claim 12, wherein the macromer solution further comprises an accelerator to increase the rate of polymerization.